

## WeatherTex weatherboards and architectural panels.

WeatherTex Weatherboards and Architectural Panels have been comprehensively tested to Australian and International Standards for verification of compliance to the Building Code of Australia.

### Material Durability Properties

The Product Specification Standard for WeatherTex is AS 1859.4 – Wet Processed Fibreboard for Exterior Conditions (HB.E)

Property	Standard	Result	Requirement
Dimensions	AS NZS 4266.2	PASS	±2mm/m
Density	AS NZS 4266.4	1000 kg/m <sup>3</sup>	> 750 kg/m <sup>3</sup>
Bending Strength	AS NZS 4266.5	32 MPa	> 20 MPa
Modulus of Elasticity	AS NZS 4266.5	4500 MPa	> 2900 MPa
Equilibrium Moisture Content	AS NZS 4266.3	7.5%	7.5% ±1% @ factory gate
Moisture Resistance	AS NZS 2457.5 – 24 Hour Submersion	< 2% Swell	8% max.
		< 6% Absorption	12.5% max.

### Thermal and acoustic properties

Property	9.5mm Component Value	WeatherTex System
Thermal Conductivity	0.195 W/mK	Where thermal and acoustically rated walls are required; WeatherTex can be used with systems detailed in the WeatherTex Install Guide to meet your specific performance requirements.
Thermal Resistance	0.05m <sup>2</sup> K/W per 9.5mm	
Acoustic Properties (Rw)	System Dependant	

### Fire properties

Property	Standard	Result	Requirement
Bushfire Attack Level (BAL)	AS 3959	Up to and including BAL 19	BCA: Vol. 2 – 3.7.4
Average Specific Extinction Area	AS/NZS 3837	38.7 m <sup>2</sup> /kg	BCA: Vol. 1 - C1.10
Material Group Number	AS/NZS 3837	Group 3	BCA: Vol. 1 - C1.10 BCA: Vol. 1 – Spec C1.10 – 4
Early Fire Hazard Indices	AS 1530.3	Ignitability: 12 Spread of Flame: 5 Heat Evolved: 4 Smoke Developed: 2	BCA: Vol. 1 - C1.10
Fire Resistance Level (FRL)	AS1530.4	60/60/60 & 90/90/90 Systems Available	BCA: Vol. 1 – Spec C1.1
Combustibility	Vol. 1 - Spec C1.1: Clause 3.10	Type A Compliant for Class 2 or 3 up to 4 story construction*	BCA: Vol. 1 – C1.1

\*WeatherTex is compliant as per Spec C1.1 for Class 2 or 3, Type A up to 3 or 4 story construction where the conditions of Clause 3.10 (a) or (b) are satisfied respectively

### Miscellaneous properties

Termite Resistance	Based on “graveyard” testing completed by CSIRO, WeatherTex products have demonstrated resistance to termites		
Formaldehyde Classification	AS/NZS 4266.16 Test Method: < 0.07 mg/L	JIS A 1460 Class: F <sup>xxxx</sup> /SE0	
	WeatherTex contains no resins, binders or added formaldehydes and the results above confirm the amount naturally present in hardwood timber is negligible and well below the acceptance level of 1.0mg/L (E1).		